

Editorial

Self-Assembled Fullerene Nanostructures at Liquid Interface

Lok Kumar Shrestha*

International Center for Materials Nanoarchitectonics (WPI-MANA), Japan

***Corresponding author:** Lok Kumar Shrestha, International Center for Materials Nanoarchitectonics (WPI-MANA), National Institute for Materials Science (NIMS), 1-1 Namiki, Tsukuba Ibaraki, 305-0044, Japan, Tel: +81 29 860 4809; Fax: +81 29 860 4832; Email: SHRESTHA.Lokkumar@nims.go.jp

Received: August 12, 2014; Accepted: August 15, 2014; Published: August 19, 2014

Fullerene is one of the most exciting nanocarbon materials. It has been widely investigated due to its interesting physical, chemical and optoelectronic properties, and has been used in diverse fields including device fabrications and drug delivery [1-3]. Prior to its discovery, diamond and graphite consisting of extended networks of sp^3 - and sp^2 -hybridized carbon atoms, respectively represented the only known allotropes of carbon for a long time. The discovery of functional molecule fullerene C_{60} in 1985 by Kroto et al. [4] changed the scenario and marked the beginning of new era of synthetic carbon allotropes. The advancement of synthetic carbons then continued rapidly enabling a success of producing carbon nanotubes in 1991 [5] followed by the rediscovery of graphene in 2004 [6]. Numerous possible carbon modifications are now being under investigation. It is anticipated that this challenge will reveal newer carbon nanostructures with fancy structure and properties in future.

Recent development in nanoscience and nanotechnology research has enabled to design functional nanomaterials whose properties can be controlled in microscopic and macroscopic length scales via self-assembly of building blocks in molecular level precision. Therefore, nanostructured assemblies have become one of the most attractive nanomaterials in tailoring of properties, arising from the confinement effects of the building blocks. Various building units have been assembled into functional nanostructures. Structural dimension is one of the useful classifications of nanostructures or nanomaterials. Interestingly the entire range of dimensionalities can be found in the nanocarbon family. Zero-dimensional (0D) fullerenes, one-dimensional (1D) nanotubes, two-dimensional (2D) graphene sheet, and three-dimensional (3D) nanocrystalline diamond and fullerite represent 0 to 3D carbon nanostructures. These are π -electron systems carbon nanostructures and depending on their dimensionality display excellent electrical, mechanical, and thermal properties and cover wider range of technological applications including anode materials for rechargeable lithium ion rechargeable batteries, optoelectronic devices, biomedicine, sensing, and catalysis [7-13].

Fullerene is an extensively studied nanomaterial in carbon family. Fullerene C_{60} is the smallest, stable and most prominent

molecular carbon allotropes consisting of a spherical network of sixty structurally equivalent sp^2 -hybridized carbon atoms in a cage lattice (diameter ~ 0.8 nm) in the shape of a soccer ball. It has truncated icosahedron symmetry, I_h , and composed of 12 pentagons and 20 hexagons with alternative single and double bonds. Furthermore, the curvature induced by the cage structure increases the energy associated with the double bonds enhancing the reactivity of the molecule. Fullerenes are therefore stable but not totally unreactive. The sp^2 -hybridized carbon atoms, which are at their energy minimum in planar graphite, must be bent to form the closed sphere, which produces angle strain. The characteristic reaction of fullerenes is electrophilic addition at 6,6-double bonds, which reduces angle strain by changing sp^2 -hybridized carbons into sp^3 -hybridized ones. One of the most intriguing features of fullerene C_{60} is its electron accepting behavior, i.e., it is an electron deficient molecule due to the presence of energetically unfavorable double bond in pentagonal rings. This property has been utilized to design bulk heterojunction in combination of suitable electron donor molecules [14,15]. Until now, this molecule has become the most popular electron acceptor material in organic solar cells due to its superior electron conductivity and efficient charge separation at electron donor/acceptor interface [16]. Particularly, in organic photovoltaics, major attention is focused to develop newer type of donor materials. Nevertheless, fullerene remains as the main acceptor material as it matches well with a wide variety of donor materials [17].

Growing interest in fullerenes has allowed exploring the many possibilities in various applications. In many designs for fullerene-based functional materials, assemblies of 0D fullerene into structures with well-defined dimension are required. Fullerene C_{60} is a 0D small isotropic spherical object and can be employed as an ideal building block for generating higher dimensional functional nanostructures [18,19]. Experiments have shown that fullerene C_{60} can be assembled into various shapes and sizes thereby advancing its optoelectronic properties compared to the bulk or pristine fullerene [20]. Among the various synthetic methods explored for the production of shape-controlled fullerene crystalline assemblies, liquid-liquid interfacial precipitation (LLIP) method has become one of the versatile methods of producing dimension-controlled nano- to micron size fullerene crystals [21]. In this method crystal formation is driven by the supersaturation related to the low C_{60} solubility in alcohols (alcohols are regarded as poor solvent or antisolvent for C_{60} as the solubility of C_{60} in alcohols is very low). Tuning solvent and antisolvent combinations, their volume ratios, temperature, and concentration, C_{60} crystalline assemblies of controlled shape and size have been produced [18]. Recent success on producing a newer type of fullerene crystals, which consist of meso- and macroporous bimodal pore architecture has opened new avenue towards the development of newer type of multifunctional fullerene [22].

Nanoporous fullerene could offer huge scientific and technological

importance owing to the presence of controllable voids of sizes in atomic, molecular, and nanometer length scales. Nanoporous fullerene with unique surface, structural, and bulk properties can underline their important uses in various fields such as energy storage, sensing, ion exchange, separation, catalysis, biological molecular isolation, and purifications. Proper doping of semiconducting nanomaterials in porous fullerenes is expected to enhance the optoelectronic properties, which is expected to enhance the performance of devices. Furthermore, micron size fullerene crystals with pore architecture could be a better scaffold for cell culture whereas the nano size porous fullerenes can be used in drug delivery. These wider applications offer exciting opportunities for researchers, engineers or biologists to develop new strategies and techniques for the synthesis and applications of nanoporous fullerene inserting multifunctionalities. Nevertheless, the remaining challenges of molecular modeling and design of nanoporous fullerenes with superior surface area and pore volume, the fundamental understanding of structure-property relations, and tailor-design of fullerene nanostructures for specific properties and applications are essential to be addressed.

Acknowledgment

LKS thanks the Japan Society for the Promotion of Science (JSPS) for the Grant-in-Aid for Young Scientists B (25790021).

References

- Saran R, Stolojan V, Curry RJ. Ultrahigh performance C60 nanorod large area flexible photoconductor devices via ultralow organic and inorganic photodoping. *Sci Rep*. 2014; 4: 5041.
- Zakharian TY, Seryshev A, Sitharaman B, Gilbert BE, Knight V, Wilson LJ, et al. A fullerene-paclitaxel chemotherapeutic: synthesis, characterization, and study of biological activity in tissue culture. *J Am Chem Soc*. 2005; 127: 12508-12509.
- Brown P, Kamat PV. Quantum dot solar cells. Electrophoretic deposition of CdSe-C60 composite films and capture of photogenerated electrons with nC60 cluster shell. *J Am Chem Soc*. 2008; 130: 8890-8891.
- Kroto HW, Heath JR, O'Beien SC, Curl RF, Smalley RE. C60: Buckminsterfullerene. *Nature* 1985; 318: 162-163.
- Iijima S. Helical microtubules of graphitic carbon. *Nature* 1991; 354:56-58.
- Novoselov KS, Geim AK, Morozov SV, Jiang D, Zhang Y, Dubonos SV, et al. Electric field effect in atomically thin carbon films. *Science*. 2004; 306: 666-669.
- Kucinskis G, Bajars G, Kleperis J. Graphene in lithium ion battery cathode materials: A review. *J. Power Sources*. 2013; 240: 66-79.
- Wang T, Pearson AJ, Lidzey DG, Jones RA. Evolution of structure, optoelectronic properties, and device performance of polythiophene: fullerene solar cells during thermal annealing. *Adv. Funt. Mater*. 2011; 21: 1383-1390.
- Liu Z, Sun X, Nakayama-Ratchford N, Dai H. Supramolecular chemistry on water-soluble carbon nanotubes for drug loading and delivery. *ACS Nano*. 2007; 1: 50-56.
- Zhu Y, Murali S, Cai W, Li X, Suk JW, Potts JR, et al. Graphene and graphene oxide: synthesis, properties, and applications. *Adv Mater*. 2010; 22: 3906-3924.
- Gao Y, Ma D, Wang C, Guan J, Bao X. Reduced graphene oxide as a catalyst for hydrogenation of nitrobenzene at room temperature. *Chem Commun (Camb)*. 2011; 47: 2432-2434.
- Biswas S, Drzal LT. Multilayered nanoarchitecture of graphene nanosheets and polypyrrole nanowires for high performance supercapacitor electrodes. *Chem. Mater*. 2010; 22: 5667-5671.
- Nakanishi W, Minami K, Shrestha LK, Ji Q, Hill JP, Ariga K. Bioactive nanocarbon assemblies: Nanoarchitectonics and applications. *Nanotoday*. 2014; 9: 378-394.
- Nelson J. Polymer:fullerene bulk heterojunction solar cells. *Materials today*. 2011; 14: 462-470.
- Deibel C, Dyakonov V. Polymer-fullerene bulk heterojunction solar cells. *Rep. Prog. Phys*. 2010; 73: 096401-096440.
- Guldi DM. Fullerenes: three dimensional electron acceptor materials. *Chem. Commun*. 2000; 321-327.
- Liu T, Troisi A. What makes fullerene acceptors special as electron acceptors in organic solar celles and how to replace them. *Adv. Funt. Mater*.2013; 25: 1038-1041.
- Shrestha LK, Ji Q, Mori T, Miyazawa K, Yamauchi Y, Hill JP, et al. Fullerene nanoarchitectonics: from zero to higher dimensions. *Chem Asian J*. 2013; 8: 1662-1679.
- Shrestha LK, Shrestha RG, Hill JP, Ariga K. Self-assembled fullerene nanostructures. *J Oleo Sci*. 2013; 62: 541-553.
- Shrestha LK, Hill JP, Tsuruoka T, Miyazawa K, Ariga K. Surfactant-assisted assembly of fullerene (C60) nanorods and nanotubes formed at a liquid-liquid interface. *Langmuir*. 2013; 29: 7195-7202.
- Miyazawa K, Kuwasaki Y, Obayashi A, Kuwabara M. C60 nanowhiskers formed by the liquid-liquid interfacial precipitation method. *J. Mater. Res*. 2002; 17: 83-88.
- Shrestha LK, Yamauchi Y, Hill JP, Miyazawa K, Ariga K. Fullerene crystals with bimodal pore architectures consisting of macropores and mesopores. *J Am Chem Soc*. 2013; 135: 586-589.